



Wednesday, May 04, 2011

**CERTENE™ LDF-221C****Muehlstein - Low Density Polyethylene**Units English**Action****Legend** ([Open](#))**General Information****Product Description**

LDF-221C is a certified prime resin specially designed to meet the requirements of most 1 to 3 mils thickness Blown film liner applications. LDF-221C features easy processability. Large lot size and superior lot-to-lot uniformity ensure consistent film production. Minimum recommended film thickness is 1.0 mil. LDF-221C contains medium slip and medium antiblock.

**General**

Material Status	● Commercial: Active
Availability	● North America
Additive	● Medium Antiblock ● Medium Slip
Features	● Good Processability ● Medium Antiblocking ● Low Density ● Medium Slip
Uses	● Film ● Liners
Forms	● Pellets
Processing Method	● Blown Film

**ASTM & ISO Properties<sup>1</sup>**

Physical	Nominal Value	Unit	Test Method
Density	0.921	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	1.5	mil	
Secant Modulus - 1% Secant, MD (1.5 mil)	25400	psi	ASTM D882
Secant Modulus - 1% Secant, TD (1.5 mil)	29700	psi	ASTM D882
Tensile Strength - MD (Yield, 1.5 mil)	1450	psi	ASTM D882
Tensile Strength - TD (Yield, 1.5 mil)	1450	psi	ASTM D882
Tensile Strength - MD (Break, 1.5 mil)	3630	psi	ASTM D882
Tensile Strength - TD (Break, 1.5 mil)	2760	psi	ASTM D882
Tensile Elongation - MD (Break, 1.5 mil)	350	%	ASTM D882
Tensile Elongation - TD (Break, 1.5 mil)	600	%	ASTM D882
Dart Drop Impact (1.5 mil)	85	g	ASTM D1709A
Elmendorf Tear Strength - MD (1.5 mil)	580	g	ASTM D1922
Elmendorf Tear Strength - TD (1.5 mil)	120	g	ASTM D1922

**Additional Information**

This Specimen was compression molded and was tested according to ASTM D1928 Procedure C.

**Processing Information**

Extrusion	Nominal Value	Unit
Melt Temperature	320 to 374	°F

**Notes**

<sup>1</sup> Typical properties: these are not to be construed as specifications.

The technical information, suggested uses and applications presented are made without charge and are believed to be reliable; however, the Ravago Group\* disclaims responsibility for reliance and results of use of this information. THE RAVAGO GROUP DISCLAIMS ALL WARRANTIES, EXPRESSED OR IMPLIED, CONCERNING THE PRODUCT(S) DESCRIBED HEREINABOVE, INCLUDING ANY WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. The Ravago Group expressly disclaims any statements or suggestions as being inducement. All users should rely upon their own knowledge and testing in determining product suitability. \*H. Muehlstein & Co., Inc., Channel Prime Alliance LLC, and Pegasus Polymers International, Inc. are affiliated companies collectively referred to herein as the Ravago Group. CERTENE® is a registered trademark of H. Muehlstein & Co., Inc. and used under license.