

Low Density Polyethylene

L2221F

PRODUCT DESCRIPTION

LDPE resin with good clarity

APPLICATIONS

Product used for general purpose packaging, including produce bags, food packaging, and textile packaging.

TYPICAL PROPERTIES

Properties		Typical Value	Unit	Test Method
Melt Flow Index (190°C/2.16 kg)		2.1 - 2.2	g/10 min	ASTM D1238
Density		0.921 - 0.923	g/cm ³	ASTM D1505
Tensile Strength at Break	MD	3,850 - 3,950	psi	ASTM D882
	TD	2,550 - 2,650		
Elongation at Break	MD	290 - 310	%	ASTM D882
	TD	590 - 610		
Secant Modulus (1%)	MD	21,900 - 22,100	%	ASTM D882
	TD	27,900 - 28,100		
Haze		5.7	%	ASTM D1003
Dart Drop Impact Strength, F50		124 - 126	g/mil	ASTM D1709A

ADDITIVE

Antiblock	1500 PPM
Slip	750 PPM
Other	NONE

DISCLAIMER: THIS TECHNICAL DATA SHEET SHOWS THE TYPICAL PROPERTIES AND THE DATA SHOWN ARE NOT TO BE CONSTRUED AS SPECIFICATIONS. THE DOCUMENT IS DESIGNED TO PROVIDE USERS GENERAL INFORMATION AND DOES NOT CONSTITUTE ANY WARRANTY OR QUALITY SPECIFICATION, EITHER EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE. USERS SHALL DETERMINE WHETHER THE PRODUCT IS SUITABLE FOR THEIR USE AND CAN BE USED SAFELY AND LEGALLY.