

Linear Low Density Polyethylene

LF2020CC**PRODUCT DESCRIPTION**

LLDPE hexene resin for general packaging application.

APPLICATIONS

Product used for general packaging, including industrial packaging.

TYPICAL PROPERTIES

Properties		Typical Value	Unit	Test Method
Melt Flow Index (190°C/2.16 kg)		1.0 - 1.1	g/10 min	ASTM D1238
Density		0.919 - 0.920	g/cm ³	ASTM D1505
Tensile Strength at Break	MD	49 - 51	Mpa	ASTM D882
	TD	38 - 40		
Elongation at Break	MD	740 - 760	%	ASTM D882
	TD	980 - 1020		
Haze		14.0	%	ASTM D1003
Dart Drop Impact Strength		165 - 175	g/mil	ASTM D1709

ADDITIVE

Antiblock	3,500 PPM
Slip	1,200 PPM
Other	NONE